


## UNCOATED WHITE WS FSC™ / SH6020 PLUS / WG74

### PRODUCT DESCRIPTION / BENEFITS

**Face** : Pure cellulose white paper. Wet strength treatment. FSC Certified.

**Adhesive** : Water-based permanent acrylic adhesive. Good adhesion to wet surfaces at low temperatures. Especially designed for glass containers, with excellent resistance to immersion in water/ice.

**Liner** : White supercalendered glassine paper one side siliconised. There may be slight variations in tone.



### TYPICAL USE

- Wine, Spirits & Craft Beer

### PRODUCT RECOMMENDATIONS

Product specially designed for high added value bottled in glass (wine, liquors, oil, water,....)

We recommend the reels to be wound with the face side out. Suitability for neck labels should be thoroughly checked and validated. Not suitable for very small radius. If possible, consider using a product from the Fedrigoni's neck label range for this application. In doubt contact Fedrigoni's technical support team for advice.

The test of resistance is carried out by sticking a blank (unprinted) label on a standard glass bottle. Five days after the label is stuck on, it is submerged in an ice bucket containing icy water for a minimum period of 4 hours and its resistance to immersion is checked.

### SHELF LIFE

2 years, under storage conditions as defined by FINAT section 2.5 (20-25°C, 40-50% RH). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life of the product.

## UNCOATED WHITE WS FSC™ / SH6020 PLUS / WG74

### PHYSICAL PROPERTIES / TYPICAL VALUES

#### FACE MATERIAL

##### UNCOATED WHITE WS FSC™

Grammage	90 Gr/m2	ISO 536
Thickness	104 µm	ISO 534-80
Dry Opacity	84 %	ISO 2471

#### ADHESIVE

##### SH6020 PLUS

Tack Glass	14 N	FTM9
Min Labelling temperature	+5 °C	
Usage Temperature	-10/+75 °C	

#### LINER

##### WG74

Grammage	72 Gr/m2	ISO 536
Thickness	62 µm	ISO 534-80

### QUALITY CERTIFICATIONS & APPROVALS

- FSC License code: FSC-C106281

### DISCLAIMER

Information on physico-chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. All Fedrigoni products are sold subject to terms and conditions of sale. For more information, contact your Fedrigoni sales representative. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.