

Informations Techniques UPM Raflatac

01-04-2020 FR SI

Frontal	FLEUR DE COTON IVOIRE WSA-FSC
Code de vente	CNU
Produit	Papier texturé, légèrement teinté, fini machine, résistant à l'humidité, aux alcalis et aux moisissures,
Utilisation	Un papier haute qualité idéal pour le vin et autres boissons.

Valeurs techniques moyennes

Grammage	95	g/m ²	ISO 536
Épaisseur	128	µm	ISO 534
Opacité	90	%	ISO 2471
Imprimabilité	Adapté aux méthodes d'impression en offset et par dorure à chaud. Des tests préalables sont recommandés pour les méthodes d'impression par sérigraphie, typographie et flexographie.		
Durabilité	Le produit est vendu sous l'appellation FSC Mix Credit certifié par le certificat FSC™ SGSCH-COC-004879 d'UPM Raflatac.		
Information supplémentaire	La couverture imprimée peut influencer la durée de décollement par lavage, particulièrement lorsque du vernis UV est appliqué. La grande rigidité du produit peut causer une distribution prématurée, notamment si l'alimentation de l'étiquette est étranglée ou si les barres internes à la machine possèdent des diamètres réduits. Les bobines doivent avoir un enroulement extérieur. Ce papier ne convient pas pour l'étiquetage des collerettes ni pour les produits de petit diamètre. Des tests préalables sont recommandés avec les étiquettes imprimées pour l'application prévue.		
Clause d'exclusion de responsabilité	<p>Nos recommandations sont basées sur notre expérience et notre savoir-faire actuels. L'utilisation de nos produits étant hors de nos possibilités de contrôle, nous ne pouvons être tenus responsables des dommages qui pourraient survenir lors de leur utilisation. Les utilisateurs de nos produits sont tenus de s'assurer que le produit est adapté à un usage particulier, qu'ils auront défini à leur entière discrétion. Les utilisateurs sont tenus de respecter toutes les lois en vigueur et/ou les tests exigés sur le produit fini. Les utilisateurs sont responsables de la mise sur le marché de leurs produits.</p> <p>La présente publication ne donne droit à aucune garantie, expresse ou tacite, et son usage est limité à son destinataire. La présente publication ne peut être transférée à un quelconque tiers. Nous déclinons toute responsabilité eu égard à l'utilisation de nos produits avec d'autres supports.</p> <p>Tous nos produits sont vendus conformément aux conditions générales de vente d'UPM Raflatac et leur utilisation doit être conforme à toutes les lois en vigueur.</p> <p>La présente publication remplace toutes les précédentes. Toutes les informations contenues dans le présent document peuvent être modifiées sans préavis de notre part.</p>		

UPM Raflatac Technical Information

03-04-2020 EN SI

Adhesive	RP30
Sales Code	RP30
Type	Permanent adhesive
Composition	Acrylic, waterborne
Use	Designed for permanent wine & spirits applications. Provides good adhesion to polar surfaces, tolerating fluctuations in temperature and humidity on the bottling line and during bottle storage. Also has good water-resistance during immersion in ice buckets. The stiffness of the label affects mandrel performance.

Typical technical values

Tack	15	N/25mm FTM 9
Labelling temperature min	5	°C
Service temperature min	-20	°C
Service temperature max	80	°C

Additional info Not suitable for applications where wash-off performance is needed. Formulation contains natural rubber latex.

Disclaimer The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

UPM Raflatac Technical Information

08-05-2020 EN SI

Backing	WHITE GLASSINE 85
Sales Code	02
Product	White glassine woodfree backing paper.
Use	For reelstock laminates, especially for information labelling in fanfold applications.

Typical technical values

Substance	78	g/m ²	ISO 536
Caliper	68	µm	ISO 534
Tensile strength MD	7.5	kN/m	ISO 1924
Tensile strength CD	3.2	kN/m	ISO 1924
Transparency	40	%	DIN 53147

Disclaimer The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.